HEATSHRINK TUBING Technical Data Sheet

2/1 FABRIC

Shrink Temperature 176°F (80°C)

- Highly Flexible
- Halogen Free
- Excellent Chemical Resistance
- Superior Abrasion Resistance Over A Wide Temp. Range
- **Cuts Easily With Scissors**



Material Polyolefin/Polyester

Grade H2F

					-		
Nominal	Part #	Unshrunk Diameter /mm	Shrunk Diameter /mm	Put-Ups		Available	Lbs/
Size				Bulk Spool	Shop Spool	Colors	100′
1/2″	H2F0.48BK	12	6	100′	25′	Black (BK)	1.15
3/4″	H2F0.79BK	20	10	100′	25′	Black (BK)	1.61
1″	H2F0.98BK	25	12.5	100′	25′	Black (BK)	1.71
1 3/16″	H2F1.18BK	30	15	100′	25′	Black (BK)	2.13
1 3/8″	H2F1.38BK	35	17.5	100′	25′	Black (BK)	2.35
1 1/2″	H2F1.58BK	40	20	100′	25′	Black (BK)	2.66
2″	H2F1.97BK	50	25	100′	25′	Black (BK)	3.44
2 3/8″	H2F2.36BK	60	30	100′	25′	Black (BK)	4.11
2 3/4″	H2F2.75BK	70	35	100′	25′	Black (BK)	4.69
3 1/8″	H2F3.15BK	80	40	100′	25′	Black (BK)	5.29

Fabric 2/1 Heatshrink Tubing Shrinks To ¹/2 its original diameter!

2/1 Fabric Heatshrink tubing, a unique mixture of Polyolefin and Polyester yarns which shrinks to 1/2 its original diameter, is the ideal way to form the only shrinkable fabric of its kind.

The woven construction makes this product extremely flexible and resistant to trapping water, heat and humidity. Provides outstanding abrasion, chafing and cutting protection, even at high temperatures.

Shrinkflex Fabric tubing, designed primarily to provide mechanical abrasion protection for components such as rubber hoses, plastic pipes, and harness wiring bundles. Also suitable for other applications, such as noise and rattle suppression.

Applications: mechanical abrasion protection, severe environment protection, noise and rattle protection, and flexing application.



nrinkflex

– Put-Ups –––





www.techflex.com 800.323.5140 • 973.300.9242 • fax: 973.300.9409 29 Brookfield Dr • Sparta, NJ 07871


HEATSHRINK TUBING Technical Data Sheet








Flammability Rating Non-Flame-Retardant



Lubricating Oil, Antifreeze (50% Ethylene Glycol), Brake Fluid, Engine Oil, Unleaded Gasoline, Diesel Fluid, Hydraulic Fluid, Mineral Hydraulic Fluid, **Battery Acid, Water.**



Recommended Cutting	Scissors
Colors	1
Wall Type	Single
Pliancy	Very Flexible
Abrasion Resistance	High





Measure the Shrinkflex® tubing to length and cut with a scissor. The thickness of your bundle, as well

as the desired final appearance, will determine the length of the tubing you cut. Generally, a piece 1 1/2" - 2" long will accommodate almost any need. Single wires, or smaller bundles, require shorter pieces.



Slip the Shrinkflex® tubing over the bundle and position it so that both the sleeved and unsleeved portions are

sufficiently covered. Notice the small pieces of tubing installed on single wires as part of a color coding system. *If your project requires multiple operations, always work* up from the smallest to the largest bundle.



Gently apply heat to Shrinkflex®

tubing from a heat gun, hair dryer or torch with an appropriate attachment. Keep the heat source far enough away so that hot metal or direct flame does not come in contact with the tubing, wires or sleeving. Move the heat around the bundle to prevent damaging the sleeving and to ensure that all areas of the tubing have been shrunk. Once cooled, your installation is complete.

© 2011 Techflex, Inc. - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex, Inc. is strictly forbidden. Techflex product names and logos are registered trademarks of Techflex, Inc., unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex's only obligations are those in standard terms of sale for these products and Techflex will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications. 02-11